

Data Sheet of 3473

Typical properties	Value	Unit	Standard
Mechanical			
Tensile modulus @5mm/min	15900	MPa	ISO527
Tensile strength, break @5mm/min	146	MPa	ISO527
Tensile strain, break@5mm/min	1.65	%	ISO527
Flexural Modulus	14500	MPa	ISO178
Flexural strength	201	MPa	ISO178
Impact			
Izod impact, Notched, 23°C	6.5	KJ/m ²	ISO180
Izod impact, Un-notched, 23°C	17.3	KJ/m ²	ISO180
Thermal			
HDT, 0.45MPa	275	°C	ISO75
HDT, 1.8Ma	250	°C	ISO75
Physical			
CTE (-40-150°C, flow, Plaque)	19 E-6	1/°C	ISO11359-2
CTE (-40-150°C, x-flow, Plaque)	25 E-6	1/°C	ISO11359-2
Shrinkage (Parallel)	0.2-0.3	%	SABIC method
Shrinkage (perpendicular)	0.3-0.4	%	SABIC method
Density	1.68	g/cm ³	ISO1183
MVR (320C, 5kg)	5.5	cm ³ /10 min	ISO1133
Electrical			
Dielectric constant @1.9GHz	4.25		SABIC method
Dissipation factor@1.9GHz	0.0056		SABIC method
Relative Permittivity, 5GHz	4.2		SABIC method
Dissipation factor, 5GHz	0.0063		SABIC method



Injection Molding Guidelines

Parameter Title	Typical Value	Unit
Drying Temperature	150	°C
Drying Time	4-6	Hrs
Melt Temperature	315-335	°C
Nozzle Temperature	300-335	°C
Front- Zone 3 Temperature	290-335	°C
Middle -Zone 2 Temperature	280-325	°C
Rear- Zone 1 Temperature	270-315	°C
Mold Temperature	120-180	°C

- 1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume rate are measured on injection molded samples. All samples are prepared according to ISO 294.
- 2) Only typical data for material selection purpose. Not to be used for part or tool design.

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA **DISCLAIMER : THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com>.AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS,SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN.**Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.