

XENOY™ RESIN 1731

REGION ASIA

DESCRIPTION

Impact/chemical resistant. UV-Stabilized. Excellent physical property retention in automotive exteriors and OVAD.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	61	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	120	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	93	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2340	MPa	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	667	J/m	ASTM D 256
Izod Impact, notched, -30°C	106	J/m	ASTM D 256
Izod Impact, notched, 23°C, 6.4mm	160	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	61	J	ASTM D 3763
Instrumented Impact Total Energy, -30°C	61	J	ASTM D 3763
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	115	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	107	°C	ASTM D 648
CTE, -40°C to 95°C, flow	8.28E-05	1/°C	ASTM E 831
Relative Temp Index, Elec	75	°C	UL 746B
Relative Temp Index, Mech w/impact	75	°C	UL 746B
Relative Temp Index, Mech w/o impact	75	°C	UL 746B
PHYSICAL			
Specific Gravity	1.22	-	ASTM D 792
Specific Volume	0.82	cm ³ /g	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.6 – 0.8	%	SABIC method
ELECTRICAL			
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	2	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	2	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating	1.49	mm	UL 94
INJECTION MOLDING			
Drying Temperature	110	°C	
Drying Time	4 – 6	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.02	%	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Temperature	260 – 275	°C	
Nozzle Temperature	255 – 270	°C	
Front - Zone 3 Temperature	255 – 275	°C	
Middle - Zone 2 Temperature	250 – 270	°C	
Rear - Zone 1 Temperature	245 – 265	°C	
Mold Temperature	65 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	50 – 80	%	
Vent Depth	0.013 – 0.02	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.