

# VALOX™ FR RESINS 310SEO

REGION ASIA

## DESCRIPTION

VALOX 310SEO is an unreinforced, flame retardant Polybutylene Terephthalate (PBT) injection moldable grade with excellent chemical resistance. It has a UL94V0@0.71mm and 5VA@3.0mm flame rating. This is a good candidate for thin wall applications in the electrical industry including bobbins, keyboards, switches and appliance housings.

## TYPICAL PROPERTY VALUES

Revision 20200610

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	58	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	52	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	18	%	ASTM D 638
Tensile Modulus, 5 mm/min	2820	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	101	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2620	MPa	ASTM D 790
Taber Abrasion, CS-17, 1 kg	19	mg/1000cy	SABIC method
Tensile Stress, yield, 50 mm/min	58	MPa	ISO 527
Tensile Stress, break, 50 mm/min	40	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5	%	ISO 527
Tensile Strain, break, 50 mm/min	18	%	ISO 527
Tensile Modulus, 1 mm/min	2800	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	90	MPa	ISO 178
Flexural Modulus, 2 mm/min	2600	MPa	ISO 178
Ball Indentation Hardness, H358/30	105	MPa	ISO 2039-1
Hardness, Rockwell R	120	-	ISO 2039-2
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	NB	J/m	ASTM D 4812
Izod Impact, notched, 23°C	40	J/m	ASTM D 256
Izod Impact, notched, -30°C	25	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	200	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	NB	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	4	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	8	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Impact, notched, 23°C	5	kJ/m <sup>2</sup>	ISO 179/2C
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	4	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m <sup>2</sup>	ISO 179/1eU
<b>THERMAL</b>			
Vicat Softening Temp, Rate B/50	170	°C	ASTM D 1525

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 1.82 MPa, 3.2mm, unannealed	74	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	162	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	71	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.92E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.92E-05	1/°C	ASTM E 831
CTE, 60°C to 138°C, flow	1.31E-04	1/°C	ASTM E 831
Thermal Conductivity	0.24	W/m·°C	ISO 8302
CTE, -40°C to 40°C, flow	7.6E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	7.3E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, flow	1.E-04	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.E-04	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	212	°C	ISO 306
Vicat Softening Temp, Rate B/50	170	°C	ISO 306
Vicat Softening Temp, Rate B/120	170	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	150	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	60	°C	ISO 75/Ae
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	73	°C	ISO 75/Af
Relative Temp Index, Elec	120	°C	UL 746B
Relative Temp Index, Mech w/impact	120	°C	UL 746B
Relative Temp Index, Mech w/o impact	140	°C	UL 746B
<b>PHYSICAL</b>			
Specific Gravity	1.4	-	ASTM D 792
Specific Volume	0.71	cm <sup>3</sup> /g	ASTM D 792
Mold Shrinkage on Tensile Bar, flow	1.1 – 1.8	%	SABIC method
Mold Shrinkage, flow, 3.2 mm	1.5 – 2.3	%	SABIC method
Mold Shrinkage, flow, 0.75-2.3 mm	0.9 – 1.6	%	SABIC method
Mold Shrinkage, flow, 2.3-4.6 mm	1.5 – 2.3	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow	0.9 – 1.9	%	SABIC method
Mold Shrinkage, xflow, 0.75-2.3 mm	1 – 1.7	%	SABIC method
Mold Shrinkage, xflow, 2.3-4.6 mm	1.6 – 2.4	%	SABIC method
Melt Flow Rate, 250°C/2.16 kgf	8.6	g/10 min	ASTM D 1238
Density	1.4	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/saturated)	0.36	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.08	%	ISO 62
Melt Volume Rate, MVR at 250°C/2.16 kg	8	cm <sup>3</sup> /10 min	ISO 1133
<b>ELECTRICAL</b>			
Dielectric Strength, in air, 3.2 mm	18.4	kV/mm	ASTM D 149
Dielectric Strength, in oil, 1.6 mm	24	kV/mm	ASTM D 149
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	2	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
High Voltage Arc Resistance {PLC}	6	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
Volume Resistivity	>1.E+15	Ohm-cm	IEC 60093

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, shorttime, 1.0mm	18	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 0.8 mm	35	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	25	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	IEC 60243-1
Relative Permittivity, 100 Hz	3.1	-	IEC 60250
Relative Permittivity, 1 MHz	2.8	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.001	-	IEC 60250
Dissipation Factor, 100 Hz	0.002	-	IEC 60250
Dissipation Factor, 1 MHz	0.0125	-	IEC 60250
Comparative Tracking Index	175	V	IEC 60112
Comparative Tracking Index, M	100	V	IEC 60112
Relative Permittivity, 50/60 Hz	2.9	-	IEC 60250
<b>FLAME CHARACTERISTICS</b>			
UL Yellow Card Link	<a href="#">E207780-636460</a>	-	-
UL Recognized, 94V-0 Flame Class Rating	0.71	mm	UL 94
UL Recognized, 94-5VA Flame Class Rating	3	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	1	mm	IEC 60695-2-12
Oxygen Index (LOI)	30	%	ISO 4589
<b>INJECTION MOLDING</b>			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	12	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	245 – 260	°C	
Nozzle Temperature	240 – 255	°C	
Front - Zone 3 Temperature	245 – 260	°C	
Middle - Zone 2 Temperature	240 – 255	°C	
Rear - Zone 1 Temperature	230 – 250	°C	
Mold Temperature	50 – 75	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 100	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.013 – 0.025	mm	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.