

NORYL™ RESIN PX1134

REGION EUROPE

DESCRIPTION

NORYL PX1134 is an unfilled material with a Vicat B/120 of 120°C according ISO 306. NORYL PX1134 offers improved impact performance to meet the standard ECE dashboard impact tests in the automotive industry. Available in several colours, which meet the various automotive standards for interior colours.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Taber Abrasion, CS-17, 1 kg	65	mg/1000cy	SABIC method
Tensile Stress, yield, 50 mm/min	40	MPa	ISO 527
Tensile Stress, break, 50 mm/min	40	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3	%	ISO 527
Tensile Strain, break, 50 mm/min	40	%	ISO 527
Tensile Modulus, 1 mm/min	2100	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	85	MPa	ISO 178
Flexural Modulus, 2 mm/min	1900	MPa	ISO 178
Hardness, H358/30	80	MPa	ISO 2039-1
IMPACT			
Izod Impact, notched 80*10*4 +23°C	18	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	10	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	19	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	14	kJ/m ²	ISO 179/1eA
THERMAL			
Thermal Conductivity	0.23	W/m°C	ISO 8302
CTE, 23°C to 80°C, flow	7.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	9.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	130	°C	ISO 306
Vicat Softening Temp, Rate B/50	115	°C	ISO 306
Vicat Softening Temp, Rate B/120	125	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	120	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	105	°C	ISO 75/Ae
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow	0.5 – 0.7	%	SABIC method
Density	1.06	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.14	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.06	%	ISO 62
Melt Volume Rate, MVR at 280°C/5.0 kg	10	cm ³ /10 min	ISO 1133
ELECTRICAL			
Volume Resistivity	1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.6	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.0004	-	IEC 60250
Dissipation Factor, 1 MHz	0.0009	-	IEC 60250
Relative Permittivity, 50/60 Hz	2.7	-	IEC 60250
FLAME CHARACTERISTICS			
UL Compliant, 94HB Flame Class Rating	1.6	mm	UL 94 by SABIC-IP
INJECTION MOLDING			
Drying Temperature	100 – 120	°C	
Drying Time	2 – 3	hrs	
Melt Temperature	280 – 300	°C	
Nozzle Temperature	260 – 280	°C	
Front - Zone 3 Temperature	280 – 300	°C	
Middle - Zone 2 Temperature	260 – 280	°C	
Rear - Zone 1 Temperature	240 – 260	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	80 – 120	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.