

NORYL™ RESIN NH7112

REGION ASIA

DESCRIPTION

NORYL NH7112 resin is a 10% glass reinforced, modified PPE-PS blend. The material offers an exceptional balance of strength and dimensional stability while using non-halogenated flame retardants to achieve UL94 flame ratings. This grade can be processed via extrusion or injection molding. NORYL NH7112 is available in custom colors and may be an excellent material candidate for use in electrical and electronics markets.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	83	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	83	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	3	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	3	%	ASTM D 638
Tensile Modulus, 5 mm/min	4300	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	137	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	3750	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	85	MPa	ISO 527
Tensile Stress, break, 5 mm/min	85	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3	%	ISO 527
Tensile Strain, break, 5 mm/min	3	%	ISO 527
Tensile Modulus, 1 mm/min	4400	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	140	MPa	ISO 178
Flexural Stress, break, 2 mm/min	134	MPa	ISO 178
Flexural Modulus, 2 mm/min	4150	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	70	J/m	ASTM D 256
Izod Impact, notched, -30°C	60	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	15	J	ASTM D 3763
Izod Impact, unnotched 80°10'3 +23°C	26	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80°10'4 +23°C	24	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80°10'4 -30°C	25	kJ/m ²	ISO 180/1U
Izod Impact, notched 80°10'4 +23°C	7	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10'4 -30°C	6	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80°10'4 sp=62mm	7	kJ/m ²	ISO 179/1eA
Charpy Impact, notched, 23°C	7	kJ/m ²	ISO 179/2C
Charpy -30°C, V-notch Edgew 80°10'4 sp=62mm	6	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80°10'4 sp=62mm	31	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80°10'4 sp=62mm	31	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate B/50	148	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	138	°C	ASTM D 648
CTE, -40°C to 40°C, flow	5.5E-04	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.8E-05	1/°C	ASTM E 831

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, -40°C to 40°C, flow	5.5E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.8E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	148	°C	ISO 306
Vicat Softening Temp, Rate B/120	150	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	137	°C	ISO 75 /Af
Relative Temp Index, Elec	110	°C	UL 746B
Relative Temp Index, Mech w/impact	105	°C	UL 746B
Relative Temp Index, Mech w/o impact	110	°C	UL 746B
PHYSICAL			
Specific Gravity	1.16	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.2 – 0.4	%	SABIC method
Melt Flow Rate, 280°C/5.0 kgf	6.5	g/10 min	ASTM D 1238
Density	1.17	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.22	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.07	%	ISO 62
Melt Volume Rate, MVR at 300°C/5.0 kg	14	cm ³ /10 min	ISO 1133
ELECTRICAL			
Dielectric Strength, in oil, 3.2 mm	25	kV/mm	ASTM D 149
Relative Permittivity, 1 MHz	2.93	-	ASTM D 150
Dissipation Factor, 1 MHz	0.0034	-	ASTM D 150
Hot Wire Ignition {PLC}	1	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	1	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	4	PLC Code	UL 746A
Volume Resistivity	>1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>3.E+17	Ohm	IEC 60093
Dielectric Strength, in oil, 3.2 mm	16	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.9	-	IEC 60250
Dissipation Factor, 1 MHz	0.0034	-	IEC 60250
FLAME CHARACTERISTICS			
UL Compliant, 94V-1 Flame Class Rating	1	mm	UL 94 by SABIC-IP
UL Compliant, 94-5VA Rating	2.5	mm	UL 94 by SABIC-IP
Glow Wire Flammability Index 960°C, passes at	1	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 2.0 mm	800	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm	800	°C	IEC 60695-2-13
INJECTION MOLDING			
Drying Temperature	100 – 120	°C	
Drying Time	2 – 3	hrs	
Melt Temperature	280 – 300	°C	
Nozzle Temperature	260 – 280	°C	
Front - Zone 3 Temperature	280 – 300	°C	
Middle - Zone 2 Temperature	260 – 280	°C	
Rear - Zone 1 Temperature	240 – 260	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Hopper Temperature	60 – 80	°C	
Mold Temperature	80 – 120	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.