

# LNP<sup>TM</sup> KONDUIT<sup>TM</sup> COMPOUND PX11311

PX11311  
REGION ASIA

## DESCRIPTION

LNP KONDUIT PX11311 is a compound based on PA6 resin containing mineral and glass fiber. Added features include thermally conductive, electrically isolative and non-brominated, non-chlorinated FR.

## TYPICAL PROPERTY VALUES

Revision 20200305

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, brk, Type I, 5 mm/min	52	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2	%	ASTM D 638
Tensile Modulus, 5 mm/min	7240	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	76	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	9040	MPa	ASTM D 790
Impact Strength	5.3 – 18.2	kJ/m <sup>2</sup>	ISO R179
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	183	J/m	ASTM D 4812
Izod Impact, notched, 23°C	43	J/m	ASTM D 256
<b>THERMAL</b>			
HDT, 1.82 MPa, 6.4 mm, unannealed	199	°C	ASTM D 648
CTE, -40°C to 40°C, flow	3.13E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	4.59E-05	1/°C	ASTM E 831
CTE, 40°C to 120°C, flow	1.94E-05	1/°C	ASTM E 831
CTE, 40°C to 120°C, xflow	6.95E-05	1/°C	ASTM E 831
Specific Heat	1.42	J/g·°C	ASTM C 351
Thermal Conductivity through-plane, 10*10*3mm sample	1.2	W/m-K	ASTM E 1461-07
Thermal Conductivity in-plane, 725*0.4mm disc	2.1	W/m-K	ASTM E 1461-07
Thermal Conductivity through-plane, 780*3mm discs	0.99	W/m-K	ISO 22007-2
Thermal Conductivity in-plane, 780*3mm discs	1.38	W/m-K	ISO 22007-2
Relative Temp Index, Elec <sup>(1)</sup>	65	°C	UL 746B
Relative Temp Index, Mech w/impact <sup>(1)</sup>	65	°C	UL 746B
Relative Temp Index, Mech w/o impact <sup>(1)</sup>	65	°C	UL 746B
<b>PHYSICAL</b>			
Density	1.74	g/cm <sup>3</sup>	ASTM D 792
Mold Shrinkage, flow, 24 hrs	0.33	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	0.48	%	ASTM D 955
Water Absorption, 23°C/24hrs	0.25	%	SABIC method
Moisture Absorption (23°C / 50% RH)	0.04	%	ISO 62
Melt Volume Rate, MVR at 300°C/10.0 kg	49	cm <sup>3</sup> /10 min	ISO 1133
<b>ELECTRICAL</b>			
Surface Resistivity	>1.E+15	Ohm	ASTM D 257
Dielectric Strength, in oil, 1.0 mm	>10	kV/mm	ASTM D 149

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Dielectric Constant (Dk), 1.1 GHz	4.74	-	ASTM ES 7-83
Dissipation Factor (Df), 1.1 GHz	0.0077	-	ASTM ES 7-83
Comparative Tracking Index <sup>(2)</sup>	600	V	IEC 60112
Comparative Tracking Index (UL) {PLC}	0	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 0	≥3	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 2	≥1	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 0	≥1	mm	UL 746A
<b>FLAME CHARACTERISTICS <sup>(1)</sup></b>			
UL Yellow Card Link	<a href="#">E207780-101041511</a>	-	-
UL Recognized, 94V-0 Flame Class Rating	≥1	mm	UL 94
Glow Wire Ignitability Temperature, 1.0 mm	775	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm	850	°C	IEC 60695-2-13
Glow Wire Flammability Index, 3.0 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.0 mm	960	°C	IEC 60695-2-12
<b>INJECTION MOLDING</b>			
Drying Temperature	80	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	270 – 295	°C	
Front - Zone 3 Temperature	270 – 290	°C	
Middle - Zone 2 Temperature	270 – 290	°C	
Rear - Zone 1 Temperature	260 – 275	°C	
Mold Temperature	85 – 100	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	20 – 60	rpm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(2) Value shown here is based on internal measurement.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.