

LNPTM KONDUITTM COMPOUND PX13322

DESCRIPTION

LNP KONDUIT PX13322 is a compound based on PA6 resin containing mineral and glass fiber. Added features include thermally conductive, electrically isolative and non-brominated, non-chlorinated FR.

TYPICAL PROPERTY VALUES

Revision 20200521

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	77	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	0.7	%	ASTM D 638
Tensile Modulus, 5 mm/min	13700	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	127	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	11000	MPa	ASTM D 790
Tensile Stress, break, 5 mm/min	78	MPa	ISO 527
Tensile Strain, break, 5 mm/min	0.8	%	ISO 527
Tensile Modulus, 1 mm/min	13000	MPa	ISO 527
Flexural Stress, break, 2 mm/min	128	MPa	ISO 178
Flexural Modulus, 2 mm/min	12000	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	235	J/m	ASTM D 4812
Izod Impact, notched, 23°C	21	J/m	ASTM D 256
Izod Impact, unnotched 80°10°4 +23°C	16	kJ/m ²	ISO 180/1U
Izod Impact, notched 80°10°4 +23°C	3	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm	205	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	174	°C	ASTM D 648
CTE, -40°C to 40°C, flow	3.08E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	4.77E-05	1/°C	ASTM E 831
CTE, 40°C to 120°C, flow	2.35E-05	1/°C	ASTM E 831
CTE, 40°C to 120°C, xflow	5.25E-05	1/°C	ASTM E 831
Thermal Conductivity through-plane, 60°60°3mm plaque	1	W/m-K	ISO 22007-2
Thermal Conductivity in-plane, 60°60°3mm plaque	3.3	W/m-K	ISO 22007-2
Thermal Conductivity through-plane, 10°10°3mm sample	2	W/m-K	ASTM E 1461-07
Thermal Conductivity in-plane, 25°0.4mm disc	3.4	W/m-K	ASTM E 1461-07
HDT/Bf, 0.45 MPa Flatw 80°10°4 sp=64mm	204	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80°10°4 sp=64mm	162	°C	ISO 75/Af
Relative Temp Index, Elec ⁽¹⁾	65	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽¹⁾	65	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽¹⁾	65	°C	UL 746B
PHYSICAL			
Density	1.69	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs	0.54	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	0.57	%	ASTM D 955

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Water Absorption, 23°C/24hrs	0.06	%	ISO 62-1
ELECTRICAL			
Surface Resistivity	>1.E+15	Ohm	ASTM D 257
Dielectric Strength, in oil, 1.0 mm	>10	kV/mm	ASTM D 149
Dielectric Constant (Dk), 1.1 GHz	4.86	-	ASTM ES 7-83
Dissipation Factor (Df), 1.1 GHz	0.0103	-	ASTM ES 7-83
Comparative Tracking Index ⁽²⁾	600	V	IEC 60112
Hot-Wire Ignition (HWI), PLC 0	≥1	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 1	≥0.8	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 0	≥0.8	mm	UL 746A
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link	E207780-101694795	-	-
UL Recognized, 94V-0 Flame Class Rating	≥0.8	mm	UL 94
Glow Wire Ignitability Temperature, 1.0 mm	800	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm	850	°C	IEC 60695-2-13
Glow Wire Flammability Index, 1.0 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3.0 mm	960	°C	IEC 60695-2-12
INJECTION MOLDING			
Drying Temperature	80	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	270 – 295	°C	
Front - Zone 3 Temperature	270 – 290	°C	
Middle - Zone 2 Temperature	270 – 290	°C	
Rear - Zone 1 Temperature	260 – 275	°C	
Mold Temperature	85 – 100	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	20 – 60	rpm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(2) Value shown here is based on internal measurement.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.