

LNPTM LUBRICOMPTM COMPOUND OFL36A

OFL-4036
REGION ASIA

DESCRIPTION

LNP LUBRICOMP OFL36A is a compound based on PPS - Branched resin containing 30% Glass Fiber, 15% PTFE. Added features of this material include: Wear Resistant.

TYPICAL PROPERTY VALUES

Revision 20200610

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, break	144	MPa	ASTM D 638
Tensile Strain, break	1.7	%	ASTM D 638
Tensile Modulus, 50 mm/min	12340	MPa	ASTM D 638
Flexural Stress	199	MPa	ASTM D 790
Flexural Modulus	11030	MPa	ASTM D 790
Tensile Stress, break	124	MPa	ISO 527
Tensile Strain, break	1.4	%	ISO 527
Tensile Modulus, 1 mm/min	11100	MPa	ISO 527
Flexural Stress	197	MPa	ISO 178
Flexural Modulus	10950	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	550	J/m	ASTM D 4812
Izod Impact, notched, 23°C	85	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	3	J	ASTM D 3763
Multiaxial Impact	1	J	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	26	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	7	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	268	°C	ASTM D 648
CTE, -40°C to 40°C, flow	2.34E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	4.86E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	2.36E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	5.01E-05	1/°C	ISO 11359-2
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	266	°C	ISO 75/Af
Relative Temp Index, Elec ⁽¹⁾	200	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽¹⁾	130	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽¹⁾	130	°C	UL 746B
PHYSICAL			
Density	1.69	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs	0.1 – 0.2	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	0.3 – 0.5	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs	0.13 – 0.18	%	ISO 294
Mold Shrinkage, xflow, 24 hrs	0.3 – 0.48	%	ISO 294

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Wear Factor Washer	33	10 ⁻¹⁰ in ⁴ -min/ft-lb-hr	ASTM D 3702 Modified: Manual
Dynamic COF	0.44	-	ASTM D 3702 Modified: Manual
Static COF	0.35	-	ASTM D 3702 Modified: Manual
Density	1.69	g/cm ³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.04	%	ISO 62
ELECTRICAL			
Comparative Tracking Index (UL) {PLC}	4	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 0	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 0	≥1.5	mm	UL 746A
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC}	7	PLC Code	ASTM D 495
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link	E207780-101282823	-	-
UL Yellow Card Link 2	E207780-101343867	-	-
UL Recognized, 94V-0 Flame Class Rating	≥0.75	mm	UL 94
INJECTION MOLDING			
Drying Temperature	120 – 150	°C	
Drying Time	4	hrs	
Melt Temperature	315 – 320	°C	
Front - Zone 3 Temperature	330 – 345	°C	
Middle - Zone 2 Temperature	320 – 330	°C	
Rear - Zone 1 Temperature	305 – 315	°C	
Mold Temperature	140 – 165	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.