

NORYL GTX™ RESIN GTX810

REGION ASIA

DESCRIPTION

10% Glass Reinforced PPE+PA Alloy.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	89	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	88	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	10	%	ASTM D 638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	155	MPa	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	3960	MPa	ASTM D 790
Hardness, Rockwell R	119	-	ASTM D 785
IMPACT			
Izod Impact, notched, 23°C	80	J/m	ASTM D 256
Izod Impact, notched, -30°C	53	J/m	ASTM D 256
THERMAL			
Vicat Softening Temp, Rate B/50	240	°C	ASTM D 1525
HDT, 0.45 MPa, 6.4 mm, unannealed	245	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	210	°C	ASTM D 648
CTE, -20°C to 150°C, flow	0.0000396 – 0.0000504	1/°C	ASTM E 831
Relative Temp Index, Elec	50	°C	UL 746B
Relative Temp Index, Mech w/impact	50	°C	UL 746B
Relative Temp Index, Mech w/o impact	50	°C	UL 746B
PHYSICAL			
Specific Gravity	1.16	-	ASTM D 792
Density	1.162	g/cm ³	ASTM D 792
Water Absorption, 50% RH, equilib	1	%	ASTM D 570
Moisture Absorption, 50% RH, 24 hrs	0.5	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.6 – 0.8	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.65 – 0.85	%	SABIC method
ELECTRICAL			
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D 495
Hot Wire Ignition {PLC}	0	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	3	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	0	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating	1.47	mm	UL 94
INJECTION MOLDING			
Drying Temperature	95 – 105	°C	
Drying Time	3 – 4	hrs	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.07	%	
Minimum Moisture Content	0.02	%	
Melt Temperature	280 – 305	°C	
Nozzle Temperature	280 – 305	°C	
Front - Zone 3 Temperature	275 – 305	°C	
Middle - Zone 2 Temperature	270 – 305	°C	
Rear - Zone 1 Temperature	265 – 305	°C	
Mold Temperature	75 – 120	°C	
Back Pressure	0.3 – 1.4	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 50	%	
Vent Depth	0.013 – 0.038	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.