

# LNPTM STAT-KONTM COMPOUND LCF1506

REGION ASIA

## DESCRIPTION

LNPTM STAT-KONTM LCF1506 compound is a 15% carbon fiber, 6% PTFE reinforced polycarbonate.

## TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 5 mm/min	111	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	111	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	4.1	%	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	160	MPa	ASTM D 790
Flexural Stress, brk, 2.6 mm/min, 100 mm span	154	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	9080	MPa	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	8410	MPa	ASTM D 790
K-factor xE-10, PV=2000 psi-fpm vs Steel	1000	-	SABIC method
Coefficient of Friction on steel, Static	0.41	-	ASTM D 1894
Coefficient of Friction on steel, Kinetic	0.19	-	ASTM D 1894
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	283	J/m	ASTM D 4812
Izod Impact, notched, 23°C	53	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	11	J	ASTM D 3763
<b>THERMAL</b>			
HDT, 0.45 MPa, 3.2 mm, unannealed	141	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	137	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	144	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	139	°C	ASTM D 648
Relative Temp Index, Elec	80	°C	UL 746B
Relative Temp Index, Mech w/impact	80	°C	UL 746B
Relative Temp Index, Mech w/o impact	80	°C	UL 746B
<b>PHYSICAL</b>			
Specific Gravity	1.31	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.05 – 0.15	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.2 – 0.3	%	SABIC method
<b>ELECTRICAL</b>			
Surface Resistivity	1.E+04	Ohm	ASTM D 257
Static Decay, 5000V to <50V	0.01	< seconds	FTMS101B
<b>FLAME CHARACTERISTICS</b>			
UL Recognized, 94V-0 Flame Class Rating	1.49	mm	UL 94



## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.