

VALOX™ RESIN 325FC

REGION ASIA

DESCRIPTION

Commercial, VALOX 325FC is compliant with food contact regulations. VALOX 325FC is a general purpose, unreinforced PBT injection moulding resin which contains internal mold release. This new 325FC grade is a good processable resin that exhibits faster and more economical cycle times.

TYPICAL PROPERTY VALUES

Revision 20180906

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--|----------------|-------------------|----------------|
| MECHANICAL | | | |
| Tensile Stress, yld, Type I, 50 mm/min | 60 | MPa | ASTM D 638 |
| Tensile Stress, brk, Type I, 50 mm/min | 60 | MPa | ASTM D 638 |
| Tensile Strain, yld, Type I, 50 mm/min | 7 | % | ASTM D 638 |
| Tensile Strain, brk, Type I, 50 mm/min | 15 | % | ASTM D 638 |
| Tensile Modulus, 50 mm/min | 2500 | MPa | ASTM D 638 |
| Tensile Stress, yield, 50 mm/min | 60 | MPa | ISO 527 |
| Tensile Stress, break, 50 mm/min | 60 | MPa | ISO 527 |
| Tensile Strain, yield, 50 mm/min | 10 | % | ISO 527 |
| Tensile Strain, break, 50 mm/min | 15 | % | ISO 527 |
| Tensile Modulus, 1 mm/min | 2550 | MPa | ISO 527 |
| Flexural Stress, yield, 2 mm/min | 85 | MPa | ISO 178 |
| Flexural Modulus, 2 mm/min | 2400 | MPa | ISO 178 |
| Hardness, H358/30 | 145 | MPa | ISO 2039-1 |
| Hardness, Rockwell R | 117 | - | ISO 2039-2 |
| IMPACT | | | |
| Charpy Impact, unnotched, 23°C | NB | kJ/m ² | ISO 179/2C |
| Charpy Impact, unnotched, -30°C | 80 | kJ/m ² | ISO 179/2C |
| Izod Impact, unnotched, 23°C | NB | J/m | ASTM D 4812 |
| Izod Impact, unnotched, -30°C | NB | J/m | ASTM D 4812 |
| Izod Impact, notched, 23°C | 38 | J/m | ASTM D 256 |
| Izod Impact, notched, 0°C | 36 | J/m | ASTM D 256 |
| Izod Impact, notched, -30°C | 36 | J/m | ASTM D 256 |
| Izod Impact, unnotched 80*10*4 +23°C | NB | kJ/m ² | ISO 180/1U |
| Izod Impact, unnotched 80*10*4 -30°C | 100 | kJ/m ² | ISO 180/1U |
| Izod Impact, notched 80*10*4 +23°C | 4 | kJ/m ² | ISO 180/1A |
| Izod Impact, notched 80*10*4 0°C | 4 | kJ/m ² | ISO 180/1A |
| Izod Impact, notched 80*10*4 -30°C | 4 | kJ/m ² | ISO 180/1A |
| Charpy Impact, notched, 23°C | 4 | kJ/m ² | ISO 179/2C |
| Charpy Impact, notched, -30°C | 4 | kJ/m ² | ISO 179/2C |
| THERMAL | | | |
| Vicat Softening Temp, Rate A/50 | 220 | °C | ASTM D 1525 |
| Vicat Softening Temp, Rate B/50 | 185 | °C | ASTM D 1525 |
| Ball Pressure Test, 125°C +/- 2°C | PASSES | - | IEC 60695-10-2 |
| Vicat Softening Temp, Rate A/50 | 220 | °C | ISO 306 |

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--|----------------|-------------------------|--------------|
| Vicat Softening Temp, Rate B/50 | 185 | °C | ISO 306 |
| Vicat Softening Temp, Rate B/120 | 185 | °C | ISO 306 |
| HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm | 150 | °C | ISO 75/Bf |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm | 50 | °C | ISO 75/Af |
| PHYSICAL | | | |
| Specific Gravity | 1.31 | - | ASTM D 792 |
| Mold Shrinkage on Tensile Bar, flow | 2 – 2.6 | % | SABIC method |
| Mold Shrinkage on Tensile Bar, xflow | 0.9 – 1.8 | % | SABIC method |
| Density | 1.31 | g/cm ³ | ISO 1183 |
| Water Absorption, (23°C/sat) | 0.34 | % | ISO 62 |
| Moisture Absorption (23°C / 50% RH) | 0.08 | % | ISO 62 |
| Melt Volume Rate, MVR at 250°C/2.16 kg | 20 | cm ³ /10 min | ISO 1133 |
| Melt Volume Rate, MVR at 250°C/5.0 kg | 50 | cm ³ /10 min | ISO 1133 |
| Melt Viscosity, 260°C, 1500 sec-1 | 165 | Pa-s | ISO 11443 |
| INJECTION MOLDING | | | |
| Drying Temperature | 110 – 120 | °C | |
| Drying Time | 2 – 4 | hrs | |
| Maximum Moisture Content | 0.02 | % | |
| Melt Temperature | 250 – 270 | °C | |
| Nozzle Temperature | 240 – 260 | °C | |
| Front - Zone 3 Temperature | 245 – 265 | °C | |
| Middle - Zone 2 Temperature | 240 – 255 | °C | |
| Rear - Zone 1 Temperature | 230 – 245 | °C | |
| Hopper Temperature | 40 – 60 | °C | |
| Mold Temperature | 40 – 100 | °C | |

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.