

CYCOLOY™ RESIN HC1204HF

REGION AMERICAS

DESCRIPTION

High heat PC/ABS blend offering good flow and excellent impact. For medical devices and pharmaceutical applications. Healthcare management of change, biocompatible (ISO10993 or USP Class VI).

TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	57	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	47	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	100	%	ASTM D 638
Tensile Modulus, 5 mm/min	2270	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	88	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2300	MPa	ASTM D 790
Taber Abrasion, CS-17, 1 kg	63	mg/1000cy	SABIC method
Tensile Stress, yield, 5 mm/min	55	MPa	ISO 527
Tensile Stress, break, 5 mm/min	45	MPa	ISO 527
Tensile Stress, yield, 50 mm/min	55	MPa	ISO 527
Tensile Stress, break, 50 mm/min	45	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	5	%	ISO 527
Tensile Strain, break, 5 mm/min	100	%	ISO 527
Tensile Strain, yield, 50 mm/min	4	%	ISO 527
Tensile Strain, break, 50 mm/min	>50	%	ISO 527
Tensile Modulus, 1 mm/min	2400	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	80	MPa	ISO 178
Flexural Modulus, 2 mm/min	2300	MPa	ISO 178
Hardness, H358/30	96	MPa	ISO 2039-1
Hardness, Rockwell R	115	-	ISO 2039-2
IMPACT			
Izod Impact, notched, 23°C	580	J/m	ASTM D 256
Izod Impact, notched, -30°C	480	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	54	J	ASTM D 3763
Izod Impact, notched 80*10*3 +23°C	50	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	30	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	50	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	30	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	130	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	112	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.2E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.2E-05	1/°C	ASTM E 831

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Thermal Conductivity	0.2	W/m-°C	ISO 8302
CTE, 23°C to 60°C, flow	8.E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	8.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	126	°C	ISO 306
Vicat Softening Temp, Rate B/120	128	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	122	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	102	°C	ISO 75/Ae
Relative Temp Index, Elec	105	°C	UL 746B
Relative Temp Index, Mech w/impact	80	°C	UL 746B
Relative Temp Index, Mech w/o impact	105	°C	UL 746B
PHYSICAL			
Specific Gravity	1.15	-	ASTM D 792
Mold Shrinkage on Tensile Bar, flow	0.5 – 0.7	%	SABIC method
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 260°C/5.0 kgf	24	g/10 min	ASTM D 1238
Density	1.15	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.6	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.2	%	ISO 62
Melt Volume Rate, MVR at 260°C/2.16 kg	8	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 260°C/5.0 kg	22	cm ³ /10 min	ISO 1133
ELECTRICAL			
Volume Resistivity	>1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, in oil, 0.8 mm	35	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	25	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.7	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.002	-	IEC 60250
Dissipation Factor, 1 MHz	0.007	-	IEC 60250
Comparative Tracking Index	250	V	IEC 60112
Relative Permittivity, 50/60 Hz	2.8	-	IEC 60250
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating	1.2	mm	UL 94
UL Recognized, 94HB Flame Class Rating 2nd value	3	mm	UL 94
Glow Wire Flammability Index 650°C, passes at	1	mm	IEC 60695-2-12
Oxygen Index (LOI)	23	%	ISO 4589
INJECTION MOLDING			
Drying Temperature	100 – 110	°C	
Drying Time	2 – 4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	260 – 290	°C	
Nozzle Temperature	240 – 280	°C	
Front - Zone 3 Temperature	250 – 290	°C	
Middle - Zone 2 Temperature	250 – 290	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Rear - Zone 1 Temperature	230 – 260	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	60 – 90	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.