

CYCOLACTM RESIN INP581

REGION AMERICAS

DESCRIPTION

High flow SAN pellets. FDA compliant (part use must be at room temperature or below).

TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	48	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	60	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	1.5	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	1.9	%	ASTM D 638
Tensile Modulus, 5 mm/min	4080	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	66	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	3440	MPa	ASTM D 790
Hardness, Rockwell R	122	-	ASTM D 785
Flexural Stress, yield, 2 mm/min	36	MPa	ISO 178
Flexural Modulus, 2 mm/min	3520	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	23	J/m	ASTM D 256
Izod Impact, notched, -30°C	12	J/m	ASTM D 256
Izod Impact, notched 80°10°4 +23°C	1	kJ/m ²	ISO 180/1A
Izod Impact, notched 80°10°4 -30°C	1	kJ/m ²	ISO 180/1A
Charpy Impact, notched, 23°C	1	kJ/m ²	ISO 179/2C
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	97	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	86	°C	ASTM D 648
Vicat Softening Temp, Rate B/50	102	°C	ISO 306
Vicat Softening Temp, Rate B/120	104	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80°10°4 sp=64mm	82	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.08	-	ASTM D 792
Melt Flow Rate, 230°C/3.8 kgf	37.7	g/10 min	ASTM D 1238
Density	1.07	g/cm ³	ISO 1183
Melt Flow Rate, 220°C/10.0 kg	98	g/10 min	ISO 1133
OPTICAL			
Yellowness Index	1	-	ASTM D 1925



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.