

FLEX NORYL™ RESIN WCD891A

REGION AMERICAS

DESCRIPTION

Flexible, halogen free PPE-TPE extrusion grade ideal for applications such as wire insulation and jacket. Flame retardant performance capable of meeting UL VW1 requirements and 80C end use temperature rating as defined by UL 1581. 89 Shore A hardness. Excellent processing using standard extrusion equipment. UL 1581 tests conducted on 2.0 mm wire with 0.12 mm x 20 stranded copper conductor.

TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 50 mm/min	12	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	239	%	ASTM D 638
Flexural Modulus, 12.5 mm/min, 100 mm span	210	MPa	ASTM D 790
Hardness, Shore A, 30S reading	89	-	ASTM D 2240
Tensile Stress, break, 50 mm/min	11	MPa	ISO 527
Tensile Strain, break, 50 mm/min	219	%	ISO 527
Flexural Modulus, 12.5 mm/min	320	MPa	ISO 178
Tear strength	12	N/mm	ISO 6383
IMPACT			
Brittleness Temperature	<-40	°C	ASTM D 746
PHYSICAL			
Specific Gravity	1.08	-	ASTM D 792
Water Absorption, 23°C/48hrs	0.16	%	ASTM D 570
Melt Flow Rate, 250°C/2.16 kgf	6.9	g/10 min	ASTM D 1238
ELECTRICAL			
Volume Resistivity	5.3E+15	Ohm-cm	IEC 60093
Dielectric strength in oil, 2.0mm	25	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	3.1	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.026	-	IEC 60250
Dissipation Factor, 1 MHz	0.017	-	IEC 60250
Comparative Tracking Index	600	V	IEC 60112
Relative Permittivity, 50/60 Hz	3.6	-	IEC 60250
FLAME CHARACTERISTICS			
Smoke Density on 0.5mm plaque, Non-flame, Ds, max	69	-	ASTM E 662
Smoke Density on 0.5mm plaque, Flame, Ds, max	117	-	ASTM E 662
Glow Wire Flammability Index 850°C, passes at	3	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 3.0 mm	850	°C	IEC 60695-2-13
Oxygen Index (LOI)	26	%	ISO 4589
WIRE AND CABLE - UL 1581 TESTED ON 2.0MM WIRE WITH 0.12MMX20 STRANDED COPPER			
Tensile strength @ break	18	MPa	UL 1581
Tensile elongation @ break	250	%	UL 1581
Tensile strength @ break after 7days @113°C	19	MPa	UL 1581
Tensile elongation @ break after 7days @113°C	235	%	UL 1581

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
UL temperature rating	80	°C	UL 1581
Heat Deformation at 100°C/250g	22	%	UL 1581
VW-1	Pass	-	UL 1581
WIRE COATING EXTRUSION			
Drying Temperature	60 – 80	°C	
Drying Time	4 – 6	hrs	
Drying Time (Cumulative)	12	hrs	
Maximum Moisture Content	0.02	%	
Extruder Length/Diameter Ratio (L/D)	22:1 to 26:1	-	
Screw Speed	15 – 40	rpm	
Feed Zone Temperature	200 – 240	°C	
Middle Zone Temperatures	220 – 260	°C	
Head Zone Temperature	240 – 260	°C	
Neck Temperature	240 – 260	°C	
Cross-head Temperature	240 – 260	°C	
Die Temperature	240 – 260	°C	
Melt Temperature	240 – 260	°C	
Conductor Pre-heat Temperature	80 – 150	°C	
Screen Pack	150 – 100	-	
Cooling Water Air Gap	100 – 200	mm	
Water Bath Temperature	15 – 80	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.