

# ULTEM™ RESIN HU1004

REGION ASIA

## DESCRIPTION

High Temperature, Transparent, Polyetherimide Blend with Improved Ductility and Enhanced Hydrostability. For medical devices and pharmaceutical applications. Healthcare management of change, biocompatible (ISO 10993 or USP Class VI); food contact compliant; Steam, Gamma, EtO, and E-beam sterilizable.

| INDUSTRY   | SUB INDUSTRY  |
|------------|---|
| Healthcare | Pharmaceutical Packaging and Drug Delivery, Surgical devices, General Healthcare, Patient Testing |

## TYPICAL PROPERTY VALUES

Revision 20220721

| PROPERTIES                                   | TYPICAL VALUES | UNITS             | TEST METHODS |
|--|----------------|-------------------|--------------|
| <b>MECHANICAL</b>                            |                |                   |              |
| Tensile Stress, yld, Type I, 5 mm/min        | 95             | MPa               | ASTM D638    |
| Tensile Stress, brk, Type I, 5 mm/min        | 90             | MPa               | ASTM D638    |
| Tensile Strain, yld, Type I, 5 mm/min        | 7              | %                 | ASTM D638    |
| Tensile Strain, brk, Type I, 5 mm/min        | 85             | %                 | ASTM D638    |
| Tensile Modulus, 5 mm/min                    | 2900           | MPa               | ASTM D638    |
| Flexural Stress, yld, 1.3 mm/min, 50 mm span | 140            | MPa               | ASTM D790    |
| Flexural Modulus, 1.3 mm/min, 50 mm span     | 3000           | MPa               | ASTM D790    |
| Tensile Stress, yield, 50 mm/min             | 97             | MPa               | ISO 527      |
| Tensile Stress, break, 50 mm/min             | 80             | MPa               | ISO 527      |
| Tensile Strain, yield, 50 mm/min             | 7              | %                 | ISO 527      |
| Tensile Strain, break, 50 mm/min             | 80             | %                 | ISO 527      |
| Flexural Stress, yield, 2 mm/min             | 136            | MPa               | ISO 178      |
| Flexural Modulus, 2 mm/min                   | 2800           | MPa               | ISO 178      |
| <b>IMPACT</b>                                |                |                   |              |
| Izod Impact, notched, 23°C                   | 70             | J/m               | ASTM D256    |
| Izod Impact, Reverse Notched, 3.2 mm         | 3300           | J/m               | ASTM D256    |
| Instrumented Dart Impact Total Energy, 23°C  | 93             | J                 | ASTM D3763   |
| Instrumented Impact Total Energy, 0°C        | 99             | J                 | ASTM D3763   |
| Instrumented Impact Total Energy, -20°C      | 93             | J                 | ASTM D3763   |
| Instrumented Dart Impact Ductility, 23°C     | 100            | %                 | ASTM D3763   |
| Instrumented Dart Impact Ductility, 0°C      | 100            | %                 | ASTM D3763   |
| Instrumented Dart Impact Ductility, -20°C    | 90             | %                 | ASTM D3763   |
| Izod Impact, unnotched 80*10*4 +23°C         | NB             | kJ/m <sup>2</sup> | ISO 180/1U   |
| Izod Impact, unnotched 80*10*4 -30°C         | NB             | kJ/m <sup>2</sup> | ISO 180/1U   |
| Izod Impact, notched 80*10*4 +23°C           | 6              | kJ/m <sup>2</sup> | ISO 180/1A   |
| Izod Impact, notched 80*10*4 -30°C           | 6              | kJ/m <sup>2</sup> | ISO 180/1A   |
| Charpy Impact, notched, 23°C                 | 11             | kJ/m <sup>2</sup> | ISO 179/2C   |
| <b>THERMAL</b>                               |                |                   |              |
| HDT, 0.45 MPa, 6.4 mm, unannealed            | 214            | °C                | ASTM D648    |
| HDT, 1.82 MPa, 6.4 mm, unannealed            | 204            | °C                | ASTM D648    |

| PROPERTIES  | TYPICAL VALUES                    | UNITS                   | TEST METHODS |
|---|-----------------------------------|-------------------------|--------------|
| CTE, -20°C to 150°C, flow                           | 5.6E-05                           | 1/°C                    | ASTM E831    |
| CTE, -20°C to 150°C, xflow                          | 5.5E-05                           | 1/°C                    | ASTM E831    |
| Thermal Conductivity                                | 0.19                              | W/m·°C                  | ASTM C177    |
| CTE, 23°C to 150°C, flow                            | 5.E-05                            | 1/°C                    | ISO 11359-2  |
| CTE, 23°C to 150°C, xflow                           | 5.E-05                            | 1/°C                    | ISO 11359-2  |
| Vicat Softening Temp, Rate A/50                     | 219                               | °C                      | ISO 306      |
| Vicat Softening Temp, Rate B/50                     | 212                               | °C                      | ISO 306      |
| Vicat Softening Temp, Rate B/120                    | 212                               | °C                      | ISO 306      |
| HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm             | 205                               | °C                      | ISO 75/Be    |
| HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm             | 190                               | °C                      | ISO 75/Ae    |
| Relative Temp Index, Elec <sup>(1)</sup>            | 105                               | °C                      | UL 746B      |
| Relative Temp Index, Mech w/impact <sup>(1)</sup>   | 105                               | °C                      | UL 746B      |
| Relative Temp Index, Mech w/o impact <sup>(1)</sup> | 105                               | °C                      | UL 746B      |
| <b>PHYSICAL</b>                                     |                                   |                         |              |
| Specific Gravity                                    | 1.28                              | -                       | ASTM D792    |
| Mold Shrinkage, flow, 3.2 mm                        | 0.5 – 0.7                         | %                       | SABIC method |
| Melt Flow Rate, 337°C/6.6 kgf                       | 10                                | g/10 min                | ASTM D1238   |
| Density   | 1.28                              | g/cm <sup>3</sup>       | ISO 1183     |
| Melt Volume Rate, MVR at 360°C/5.0 kg               | 14                                | cm <sup>3</sup> /10 min | ISO 1133     |
| <b>ELECTRICAL</b>                                   |                                   |                         |              |
| Comparative Tracking Index (UL) {PLC}               | 4                                 | PLC Code                | UL 746A      |
| Hot-Wire Ignition (HWI), PLC 1                      | ≥1.5                              | mm                      | UL 746A      |
| Hot-Wire Ignition (HWI), PLC 2                      | ≥0.75                             | mm                      | UL 746A      |
| High Amp Arc Ignition (HAI), PLC 1                  | ≥0.75                             | mm                      | UL 746A      |
| <b>FLAME CHARACTERISTICS <sup>(1)</sup></b>         |                                   |                         |              |
| UL Yellow Card Link                                 | <a href="#">E121562-100737020</a> | -                       | -            |
| UL Recognized, 94V-0 Flame Class Rating             | ≥0.75                             | mm                      | UL 94        |
| Oxygen Index (LOI)                                  | 46                                | %                       | ASTM D2863   |
| NBS Smoke Density, Flaming, Ds 4 min                | 0.7                               | -                       | ASTM E662    |
| <b>INJECTION MOLDING</b>                            |                                   |                         |              |
| Drying Temperature                                  | 150                               | °C                      |              |
| Drying Time   | 6 – 8                             | Hrs                     |              |
| Drying Time (Cumulative)                            | 24                                | Hrs                     |              |
| Maximum Moisture Content                            | 0.02                              | %                       |              |
| Melt Temperature                                    | 355 – 390                         | °C                      |              |
| Nozzle Temperature                                  | 345 – 390                         | °C                      |              |
| Front - Zone 3 Temperature                          | 345 – 390                         | °C                      |              |
| Middle - Zone 2 Temperature                         | 335 – 390                         | °C                      |              |
| Rear - Zone 1 Temperature                           | 330 – 390                         | °C                      |              |
| Mold Temperature                                    | 130 – 160                         | °C                      |              |
| Back Pressure                                       | 0.3 – 0.7                         | MPa                     |              |
| Screw Speed   | 40 – 70                           | rpm                     |              |
| Shot to Cylinder Size                               | 40 – 60                           | %                       |              |
| Vent Depth  | 0.025 – 0.076                     | mm                      |              |

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.