

LEXAN™ HEALTHCARE RESIN HPS1R

REGION ASIA

DESCRIPTION

LEXAN HPS1R is a high flow polycarbonate (PC) with an MVR (300°C/1.2kg) of 23. This is a biocompatible (ISO10993 or USP Class VI) grade for medical devices and pharmaceutical applications. It is gamma and e-beam sterilizable, contains a higher amount of mold release than HPS1 and adheres to our healthcare management of change policy.

TYPICAL PROPERTY VALUES

Revision 20220721

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	65	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	6	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	120	%	ASTM D638
Tensile Modulus, 50 mm/min	2370	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	93	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2300	MPa	ASTM D790
Hardness, Rockwell M	70	-	ASTM D785
Hardness, Rockwell R	118	-	ASTM D785
Taber Abrasion, CS-17, 1 kg	10	mg/1000cy	ASTM D1044
Tensile Stress, yield, 50 mm/min	63	MPa	ISO 527
Tensile Stress, break, 50 mm/min	50	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	70	%	ISO 527
Tensile Modulus, 1 mm/min	2350	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	90	MPa	ISO 178
Flexural Modulus, 2 mm/min	2300	MPa	ISO 178
Ball Indentation Hardness, H358/30	95	MPa	ISO 2039-1
IMPACT			
Izod Impact, unnotched, 23°C	3204	J/m	ASTM D4812
Izod Impact, notched (natural, tints)	640	J/m	ASTM D256
Izod Impact, notched (colors)	106.8 – 640.8	J/m	ASTM D256
Tensile Impact Strength, Type S	378	kJ/m ²	ASTM D1822
Falling Dart Impact (D 3029), 23°C	169	J	ASTM D3029
Instrumented Dart Impact Energy @ peak, 23°C	54	J	ASTM D3763
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	12	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	10	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	12	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	10	kJ/m ²	ISO 179/1eA
THERMAL			
HDT, 0.45 MPa, 6.4 mm, unannealed	137	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	126	°C	ASTM D648

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, -40°C to 95°C, flow	6.84E-05	1/°C	ASTM E831
Specific Heat	1.25	J/g-°C	ASTM C351
Thermal Conductivity	0.19	W/m-°C	ASTM C177
Thermal Conductivity	0.2	W/m-°C	ISO 8302
CTE, 23°C to 80°C, flow	7.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	139	°C	ISO 306
Vicat Softening Temp, Rate B/120	140	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	133	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	121	°C	ISO 75/Ae
PHYSICAL			
Specific Gravity	1.2	-	ASTM D792
Specific Volume	0.83	cm³/g	ASTM D792
Density	1.19	g/cm³	ASTM D792
Water Absorption, (23°C/24hrs)	0.15	%	ASTM D570
Water Absorption, (23°C/Saturated)	0.35	%	ASTM D570
Water Absorption, equilibrium, 100°C	0.58	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	25	g/10 min	ASTM D1238
Density	1.2	g/cm³	ISO 1183
Melt Volume Rate, MVR at 300°C/1.2 kgf	23	cm³/10 min	ISO 1133
OPTICAL			
Light Transmission, 2.54 mm	88	%	ASTM D1003
Haze, 2.54 mm	1	%	ASTM D1003
Refractive Index	1.586	-	ASTM D542
ELECTRICAL			
Volume Resistivity	>1.E+17	Ω.cm	ASTM D257
Dielectric Strength, in air, 3.2 mm	14.9	kV/mm	ASTM D149
Relative Permittivity, 50/60 Hz	3.17	-	ASTM D150
Relative Permittivity, 1 MHz	2.96	-	ASTM D150
Dissipation Factor, 50/60 Hz	0.0009	-	ASTM D150
Dissipation Factor, 1 MHz	0.01	-	ASTM D150
Volume Resistivity	>1.E+15	Ω.cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ω	IEC 60093
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.7	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.001	-	IEC 60250
Dissipation Factor, 1 MHz	0.01	-	IEC 60250
Relative Permittivity, 50/60 Hz	2.7	-	IEC 60250
FLAME CHARACTERISTICS			
Oxygen Index (LOI)	25	%	ISO 4589
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	48	Hrs	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Maximum Moisture Content	0.02	%	
Melt Temperature	270 – 295	°C	
Nozzle Temperature	265 – 290	°C	
Front - Zone 3 Temperature	270 – 295	°C	
Middle - Zone 2 Temperature	260 – 280	°C	
Rear - Zone 1 Temperature	250 – 270	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.