

ULTEM™ RESIN HU2100

REGION ASIA

DESCRIPTION

10% Glass fiber filled, standard flow Polyetherimide (Tg 217C). US FDA and European Food Contact approved. For medical devices and pharmaceutical applications. Healthcare management of change, biocompatible (ISO 10993 or USP Class VI); food contact compliant; Steam, Gamma, EtO, and E-beam sterilizable.

TYPICAL PROPERTY VALUES

Revision 20180906

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	114	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	115	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	6	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	6	%	ASTM D 638
Tensile Modulus, 5 mm/min	4680	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	160	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	5500	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	115	MPa	ISO 527
Tensile Stress, break, 5 mm/min	115	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4	%	ISO 527
Tensile Strain, break, 5 mm/min	4	%	ISO 527
Tensile Modulus, 1 mm/min	4500	MPa	ISO 527
Flexural Stress, break, 2 mm/min	185	MPa	ISO 178
Flexural Modulus, 2 mm/min	4500	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	53	J/m	ASTM D 256
Izod Impact, notched, -30°C	53	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	10	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	30	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	30	kJ/m ²	ISO 180/1U
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	7	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	223	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	205	°C	ASTM D 648
CTE, -40°C to 40°C, flow	3.24E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.E-05	1/°C	ASTM E 831
CTE, 23°C to 150°C, flow	2.6E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	6.E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	212	°C	ISO 306
Vicat Softening Temp, Rate B/120	217	°C	ISO 306
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	205	°C	ISO 75/Ae
Relative Temp Index, Elec	170	°C	UL 746B
Relative Temp Index, Mech w/impact	170	°C	UL 746B
Relative Temp Index, Mech w/o impact	170	°C	UL 746B

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
PHYSICAL			
Specific Gravity	1.34	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.6	%	SABIC method
Melt Flow Rate, 200°C/3.8 kgf	5	g/10 min	ASTM D 1238
Density	1.34	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	1	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.6	%	ISO 62
Melt Volume Rate, MVR at 360°C/5.0 kg	9	cm ³ /10 min	ISO 1133
ELECTRICAL			
Dielectric Strength, in oil, 3.2 mm	15	kV/mm	IEC 60243-1
Comparative Tracking Index	150	V	IEC 60112
INJECTION MOLDING			
Drying Temperature	150	°C	
Drying Time	4 – 6	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	370 – 410	°C	
Nozzle Temperature	350 – 405	°C	
Front - Zone 3 Temperature	360 – 415	°C	
Middle - Zone 2 Temperature	350 – 405	°C	
Rear - Zone 1 Temperature	340 – 395	°C	
Hopper Temperature	80 – 120	°C	
Mold Temperature	140 – 180	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.