

ULTEM™ RESIN PW2100

REGION EUROPE

DESCRIPTION

ULTEM PW2100 resin is an amorphous, opaque, 10% glass fiber reinforced polyetherimide (PEI) plastic offering a glass transition temperature (T_g) of 217? C. This inherently flame retardant resin is KTW, WRAS, ACS, NSF-61 and W270 certified and is US FDA and European Food Contact approved. ULTEM PW2100 resin offers specific colors designed and certified for use in potable water applications.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Taber Abrasion, CS-17, 1 kg	15	mg/1000cy	SABIC method
Tensile Stress, break, 5 mm/min	115	MPa	ISO 527
Tensile Strain, break, 5 mm/min	4	%	ISO 527
Tensile Modulus, 1 mm/min	4500	MPa	ISO 527
Flexural Stress, break, 2 mm/min	185	MPa	ISO 178
Flexural Modulus, 2 mm/min	4500	MPa	ISO 178
Hardness, H358/30	140	MPa	ISO 2039-1
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	30	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	30	kJ/m ²	ISO 180/1U
Charpy Impact, notched, 23°C	7	kJ/m ²	ISO 179/2C
THERMAL			
Thermal Conductivity	0.24	W/m·°C	ISO 8302
CTE, 23°C to 150°C, flow	2.6E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	6.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	223	°C	ISO 306
Vicat Softening Temp, Rate B/50	212	°C	ISO 306
Vicat Softening Temp, Rate B/120	217	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	210	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	205	°C	ISO 75/Ae
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow	0.4 – 0.6	%	SABIC method
Density	1.34	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	1	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.6	%	ISO 62
Melt Volume Rate, MVR at 360°C/5.0 kg	9	cm ³ /10 min	ISO 1133
FLAME CHARACTERISTICS			
Oxygen Index (LOI)	46	%	ISO 4589
INJECTION MOLDING			
Drying Temperature	150	°C	
Drying Time	4 – 6	hrs	
Maximum Moisture Content	0.02	%	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Temperature	370 – 410	°C	
Nozzle Temperature	350 – 405	°C	
Front - Zone 3 Temperature	360 – 415	°C	
Middle - Zone 2 Temperature	350 – 405	°C	
Rear - Zone 1 Temperature	340 – 395	°C	
Hopper Temperature	80 – 120	°C	
Mold Temperature	140 – 180	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.