

# VALOX<sup>TM</sup> RESIN VX4915R

REGION EUROPE

## DESCRIPTION

15% Glass reinforced nucleated PBT/ASA improved release, with excellent mechanical properties high dimensional stability, and low density.

## TYPICAL PROPERTY VALUES

Revision 20200610

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 5 mm/min	85	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	85	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	3	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	3	%	ASTM D 638
Tensile Modulus, 5 mm/min	5600	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	125	MPa	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	125	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	4200	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	80	MPa	ISO 527
Tensile Stress, break, 5 mm/min	80	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4	%	ISO 527
Tensile Strain, break, 5 mm/min	4	%	ISO 527
Tensile Modulus, 1 mm/min	5700	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	130	MPa	ISO 178
Flexural Stress, break, 2 mm/min	130	MPa	ISO 178
Flexural Strain, break, 2 mm/min	4	%	ISO 178
Flexural Modulus, 2 mm/min	4600	MPa	ISO 178
Ball Indentation Hardness, H358/30	100	MPa	ISO 2039-1
Hardness, Rockwell R	120	-	ISO 2039-2
<b>IMPACT</b>			
Charpy Impact, unnotched, 23°C	45	kJ/m <sup>2</sup>	ISO 179/2C
Charpy Impact, unnotched, -30°C	30	kJ/m <sup>2</sup>	ISO 179/2C
Izod Impact, unnotched, 23°C	520	J/m	ASTM D 4812
Izod Impact, unnotched, -30°C	490	J/m	ASTM D 4812
Izod Impact, notched, 23°C	65	J/m	ASTM D 256
Izod Impact, notched, 0°C	60	J/m	ASTM D 256
Izod Impact, notched, -30°C	50	J/m	ASTM D 256
Izod Impact, unnotched 80*10*4 +23°C	35	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	25	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	6	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	5	kJ/m <sup>2</sup>	ISO 180/1A
Charpy Impact, notched, 23°C	6	kJ/m <sup>2</sup>	ISO 179/2C
Charpy Impact, notched, -30°C	6	kJ/m <sup>2</sup>	ISO 179/2C
<b>THERMAL</b>			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate A/50	213	°C	ASTM D 1525
Vicat Softening Temp, Rate B/50	135	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	200	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	105	°C	ASTM D 648
CTE, -40°C to 40°C, flow	8.29E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.22E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, flow	4.E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	1.E-04	1/°C	ISO 11359-2
CTE, 23°C to 150°C, flow	2.72E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	1.91E-04	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	213	°C	ISO 306
Vicat Softening Temp, Rate B/50	135	°C	ISO 306
Vicat Softening Temp, Rate B/120	135	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	200	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	105	°C	ISO 75/Af
<b>PHYSICAL</b>			
Specific Gravity	1.31	-	ASTM D 792
Filler Content	15	%	ASTM D 229
Mold Shrinkage on Tensile Bar, flow	0.2 – 0.6	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow	0.3 – 0.7	%	SABIC method
Melt Flow Rate, 265°C/5.0 kgf	33	g/10 min	ASTM D 1238
Density	1.31	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/saturated)	0.8	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.3	%	ISO 62
Melt Volume Rate, MVR at 250°C/5.0 kg	20	cm <sup>3</sup> /10 min	ISO 1133
Melt Volume Rate, MVR at 265°C/5.0 kg	30	cm <sup>3</sup> /10 min	ISO 1133
Melt Viscosity, 260°C, 1500 sec-1	155	Pa-s	ISO 11443
<b>ELECTRICAL</b>			
Volume Resistivity	>1.E+15	Ohm-cm	ASTM D 257
Dielectric Strength, in oil, 1.6 mm	22	kV/mm	ASTM D 149
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	ASTM D 149
Relative Permittivity, 1 MHz	3	-	ASTM D 150
Dissipation Factor, 1 MHz	0.02	-	ASTM D 150
Volume Resistivity	>1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, in oil, 1.6 mm	22	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	3	-	IEC 60250
Dissipation Factor, 1 MHz	0.02	-	IEC 60250
Comparative Tracking Index	575	V	IEC 60112
<b>INJECTION MOLDING</b>			
Drying Temperature	110 – 120	°C	
Drying Time	2 – 4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 270	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Nozzle Temperature	240 – 260	°C	
Front - Zone 3 Temperature	245 – 265	°C	
Middle - Zone 2 Temperature	240 – 255	°C	
Rear - Zone 1 Temperature	230 – 245	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	40 – 100	°C	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.